



SCHEDA TECNICA 12MY

Product description	Polyethylene Hand film
Width (testing method measuring tape)	450 mm +/- 5 mm
Length (testing method high speed encoder)	300 m +/-5 m
Thickness	12 micron +/- 1 micron
Density (testing method ASTM D-1505)	0,91-0,92 g/cm ³
Rolls per pallet (europallet)	288
Roll weight	1,71
Pallet weight	492
Total pallet height (incl. pallet) mm	1590
Ultimate stretch (testing method ESTL FPT 750)	Up to 80 %
Ultimate force (testing method ESTL FPT 750)	Up to 134,4 Newton
Puncture test (testing method ESTL FPT 750)	Maximum 53,4 Newton, Displacement 174,9mm
Tear test (testing method ESTL FPT 750)	Time to breakage 23,15 seconds
Post-consumer waste	Minimum 30 %
Post-industrial waste	Minimum 30 %
Recyclable	100 %