



**SCHEDA TECNICA 15 MY**

Product description	Polyethylene Hand film
Width (testing method measuring tape)	450 mm +/- 5 mm
Length (testing method high speed encoder)	300 m +/-5 m
Thickness	15 micron +/- 1 micron
Density (testing method ASTM D-1505)	0,91-0,92 g/cm <sup>3</sup>
Rolls per pallet (europallet)	288
Roll weight	2,13
Pallet weight	633
Total pallet height (incl. pallet) mm	1590
Ultimate stretch (testing method ESTL FPT 750)	Up to 80 %
Ultimate force (testing method ESTL FPT 750)	Up to 168 Newton
Puncture test (testing method ESTL FPT 750)	Maximum 66,75 Newton, Displacement 218,63mm
Tear test (testing method ESTL FPT 750)	Time to breakage 28,94 seconds
Post-consumer waste	Minimum 30 %
Post-industrial waste	Minimum 30 %
Recyclable	100 %